

REMARKS

Claims 1-11 are active in the present application. Claims 4, 5, 7, 9 and 10 have been amended to remove multiple dependencies. No new matter is added. An action on the merits and allowance of claims is solicited.

Respectfully submitted,

OBLON, SPIVAK, McCLELLAND,  
MAIER & NEUSTADT, P.C.



Norman F. Oblon  
Attorney of Record  
Registration No. 24,618

Stefan U. Koschmieder, Ph.D.  
Registration No. 50,238



**22850**

(703) 413-3000  
Fax #: (703)413-2220  
NFO/kst

I:\atty\SUKOS\220983us-pr.wpd

220983US-0PCT

**Marked-Up Copy**

Serial No:

Amendment Filed on:

3-26-2002IN THE CLAIMS

--4. (Amended) The hexagonal lithium-cobalt composite oxide for a lithium secondary cell according to Claim 1, [2 or 3,] wherein the packing press density of the hexagonal lithium-cobalt composite oxide is from 2.90 to 3.35 g/cm<sup>3</sup>.

5. (Amended) A process for producing the hexagonal lithium-cobalt composite oxide for a lithium secondary cell as defined in [any one of Claims 1 to 4] Claim 1, which comprises dry blending a cobalt oxyhydroxide powder having an average particle size of from 1 to 20  $\mu\text{m}$  and a specific surface area of from 2 to 200 m<sup>2</sup>/g, a lithium carbonate powder having an average particle size of from 1 to 50  $\mu\text{m}$  and a specific surface area of from 0.1 to 10 m<sup>2</sup>/g, and a powder of an oxide of metal element M having an average particle size of at most 10  $\mu\text{m}$  and a specific surface area of from 1 to 100 m<sup>2</sup>/g, and firing the mixture at a temperature of from 850 to 1,000°C in an oxygen-containing atmosphere.

7. (Amended) A positive electrode for a lithium secondary cell, which contains the hexagonal lithium-cobalt composite oxide for a lithium secondary cell as defined in [any one of Claims 1 to 4] Claim 1, as an active material.

9. (Amended) The positive electrode for a lithium secondary cell according to Claim 7 [or 8], wherein the current collector is aluminum or stainless steel.

